


## STATUS AQUAWOOD PROTECTIVE & PRESERVATIVE WATER-BASED WOOD VARNISH



### DESCRIPTION

**STATUS AQUAWOOD** is a water-based varnish. It is specially designed for contributing to the effective protection of wood, in both indoor and outdoor spaces, at the same time accentuating the natural beauty of the wood. It can be applied on all wooden surfaces, either existing or new, such as doors, windows, ceilings, casings, trellises, garden furniture, enclosures, wooden coverings, etc. Penetrates deep into the pores of the wood, offering

longer life, while it also allows wood to breathe. Odourless and fast drying, it contains anti-UV filters for protection against solar radiation. In combination with its water-repellent properties, it prevents humidity that could attract harmful insects, fungi, dry rot and several other parasites. Finally, its special composition follows wood shrinkage and expansion, without allowing any cracking or peeling to appear.

### APPLICATION FIELDS

Specially designed for contributing to the effective protection of wood, in both indoor and outdoor spaces, at the same time accentuating the natural beauty of the wood.

It enhances wood texture and offers natural shade. Applied on all wooden surfaces, either existing or new, such as doors, windows, shutters, ceilings, casings, trellises, garden furniture, enclosures, wooden coverings, etc.

### ADVANTAGES – CHARACTERISTICS

- 3 to 1: Protects, preserves and decorates.
- Contains anti-UV filters for protection against solar radiation.
- Long lifespan.
- Easily worked and uniformly spread.
- Odourless
- Strong adhesion
- Perfect impregnating properties
- Excellent water-repellent.
- Fast drying.
- Increased protection against rain and humidity.
- No leaks.
- Gel – No stains.

### SUBSTRATE PREPARATION

The surface should necessarily be dry, rigid and free from dust, mould, grease or resin before application. Humidity in the wood should not exceed 20%.

**New wood:** Remove any oil or resin with **LS-735 SOLVENT** and then treat the knots.

**Painted wood:** Remove the old paints or varnishes with

a corrosive medium and then clean the surface with **LS-735 SOLVENT**.

Repair all the defects of the wood with the appropriate stucco. Use the suitable sandpaper to smoothen the surface well in parallel with the texture streaks. Remove dust with a damp, non-fluffy cloth.

### APPLICATION

Mix the content of the container before use. Apply two layers of **STATUS AQUAWOOD** in the shade you like with the suitable brush. The use of colourless **STATUS AQUAWOOD** on exterior surfaces without previously applying one of the available shades results in reduced resistance to ultraviolet radiation. Work uniformly with the brush and avoid overlapping.

Always finish application in parallel to the wood texture streaks. Let dry well between successive layers. Smooth softly between layers and alongside the texture with soft sandpaper. For glossy or satin finish on indoor or outdoor surfaces apply 1-2 layers of **STATUS ECOVARN ECOLOGICAL WOOD VARNISH**.

## DRYING

Touch dry after 30-45 min.

## RECOATING

Recoat after 2-3 hours. Drying times refer to normal environmental conditions (25°C, humidity 60%). Any difference in environmental temperature and humidity could affect the above times.

## SHADES

Available as colourless and in 8 shades from the colour index.

## APPLICATION RATE

10-12 m<sup>2</sup>/lt on a smooth, medium absorbent surface.

## APPLICATION TOOLS

Brush, gun or airless gun.

## CLEANING OF TOOLS

Immediately after use empty the entire remaining colour into the container and clean all tools with hot water and soap. Do not pour the washing liquids on the ground.

## PACKAGING

Available in metal containers of 750ml, 2,5lt.

## DILUTION

Ready for use.

## STORAGE

After application close the container tightly to preserve in good condition for future use. It can be stored in tightly closed containers for a long time as long as it has

not been diluted. Store in cool and dry places. Protect from sun and frost.

## VOLATILE ORGANIC COMPOUNDS (VOC)

- Wood varnishes and paints for indoor and outdoor decorations (WB)
- VOC limit value: 130 gr/lt
- Maximum VOC content in product ready for use: 125 gr/lt

## APPLICATION TEMPERATURE

Avoid painting at temperatures lower than 5°C or before rain. During application the surface should not be directly exposed to sunlight. Adverse conditions during or shortly after application could affect the final properties of the product.

*The technical information and guidelines in this brochure related to the application and end-use of THRAKON products are based on the Company's current expertise and experience on the products and are given in good faith provided they are properly stored, used and applied in accordance with the guidelines given by THRAKON. Given that we are unable to directly inspect the conditions that prevail at the worksite as well as the application of the product, the Company shall not provide any guarantee regarding the suitability of its products for any particular purpose and disclaims any legal responsibility that is based on written information in this brochure or on written or oral or otherwise provided recommendations and guidelines. By applying the product on a small surface, the users are advised to test the product's suitability for the intended application and purpose. THRAKON reserves the right to amend the properties of its products without prior notice. All orders are accepted only after acceptance of the above and under the Company's respective Trade Policy terms. This version of the technical data sheet automatically cancels any previous version.*

# STATUS AQUAWOOD

## PROTECTIVE & PRESERVATIVE

## WATER-BASED WOOD VARNISH



### PRECAUTIONS

For information about safe use, storage and disposal of the product read the information on the label and in the most recent MSDS of the product, which is available upon request to the professionals.

The remains of the paints should not be disposed of together with domestic waste. Ask for advice from the local government with regard to the disposal and removal of waste.  
Poisoning Centre Tel. No.: 210 77.93.777

TECHNICAL CHARACTERISTICS	UNITS	STANDARD	VALUE
Density (20°C)	(g/ml)	EN ISO 2811.01-02	1.10 ± 0,02
Viscosity	(sec)	Flow Cup N°4	55 ± 15
Accelerated ageing through UV radiation (500h)	(°C)	ISO 11507-97	No alteration of the film is detected

**Note:** The measurements were taken in laboratory environment under a temperature of +23°C, Relative Humidity 50 % and without ventilation. They may vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation and absorbability of the substrate.