STATUS DUROMETAL HARDENER ALKYD PAINT HARDENER



DESCRIPTION

STATUS DUROMETAL HARDENER is an additional hardener for alkyd enamel paints. It provides the paint film with increased hardness within less time. Enhances resistance to impacts and friction.

Guarantees faster drying and higher tolerance to weather changes and solvents. The use of the product offers protection to the gloss of the surface and its shade even under the most adverse weather conditions.

APPLICATION FIELDS

Suitable for alkyd-based enamel paints.

ADVANTAGES - CHARACTERISTICS

- Exceptional resistance to impact and friction
- Faster drying
- Increased hardness

- Protects gloss and shade
- Higher tolerance to weather changes and solvents

APPLICATION

The product does not require any dilution during application. Use up to 20% by volume because any amount larger than the specified shall make the film hard and fragile. Mix well and apply. After the addition of the

hardener into the paint, use the mixture within 2 hours otherwise the product hardens inside the container. Close the used container tightly and store in places with low humidity.

DRYING RECOATING

Touch dry after 2-3 hours.

Recoat after 16 hours. Drying times refer to normal environmental conditions (25°C, humidity 60%). Any difference in environmental temperature and humidity could affect the above times.

APPLICATION RATE

Mix up to 20% by volume with all enamel paints.

Brush, gun, roller.

CLEANING OF TOOLS

Throughout the application, keep the tools "wet" inside the container with the paint. Remove all the paint from the tools and empty it into the container. Clean them with solvent and soapy water. After use, clean all tools with WHITE SPIRIT and then with hot water and detergent. Do not pour the washing liquids on the ground.

PACKAGING

APPLICATION TOOLS

Available in metal containers of 750ml.

Technical Support Line 800 100 14 14 support@thrakon.gr • www.thrakon.gr

STATUS DUROMETAL HARDENER



ALKYD PAINT HARDENER

APPLICATION TEMPERATURE

Atmospheric temperature should be 8–30°C and the relative humidity lower than 80%. Adverse conditions during application could alter the final properties of the paint.

STORAGE

After application close the container tightly and store in places with low humidity.

PRECAUTIONS

For information about safe use, storage and disposal of the product read the information on the label and in the most recent MSDS of the product, which is available upon request to the professionals.

The remains of the paints should not be disposed of together with domestic waste. Ask for advice from the local government with regard to the disposal and removal of waste.

Poisoning Centre Tel. No.: 210 77.93.777

TECHNICAL CHARACTERISTICS	UNITS	STANDARD	VALUE
Viscosity	(sec)	Flow Cup N°4	10±0.5
Density (20°C)	(g/ml)		0.94± 0.05

Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative Humidity 50 % and without ventilation. They may vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation and absorbability of the substrate.

The technical information and guidelines in this brochure related to the application and end-use of THRAKON products are based on the Company's current expertise and experience on the products and are given in good faith provided they are properly stored, used and applied in accordance with the guidelines given by THRAKON. Given that we are unable to directly inspect the conditions that prevail at the worksite as well as the application of the product, the Company shall not provide any guarantee regarding the suitability of its products for any particular purpose and disclaims any legal responsibility that is based on written information in this brochure or on written or oral or otherwise provided recommendations and guidelines. By applying the product on a small surface, the users are advised to test the product's suitability for the intended application and purpose. THRAKON reserves the right to amend the properties of its products without prior notice. All orders are accepted only after acceptance of the above and under the Company's respective Trade Policy terms. This version of the technical data sheet automatically cancels any previous version.