

STATUS NAUTICAL YACHT VARNISH



DESCRIPTION

STATUS NAUTICAL is an especially durable, transparent, polyurethane yacht varnish that protects and decorates all indoor and outdoor wooden surfaces. Specially designed for wooden vessels as well as front doors, casings, windows, trellises, banisters, etc. The high

content of anti-UV filters enhances its durability and protects from cracking and peeling. Ideal for wood exposed to humidity, the saltiness of the sea and increased sunlight, it forms an elastic and waterproof membrane providing long-time protection.

APPLICATION FIELDS

- Applied on all kinds of wooden surface, such as doors, windows, casings, coatings, beams, roofs, enclosures, trellises, etc.
- Suitable for wooden vessels, yachts, cruisers, etc.
- Suitable for both indoor and outdoor use.

ADVANTAGES – CHARACTERISTICS

- Suitable for protecting wooden surfaces from the salts and the iodine of the sea.
- Protects from humidity and rain.
- Protects the paint film from fungi and decay.
- Protects from ultraviolet (UV) radiation.
- High elasticity and resistance to cuts.
- Follows the shrinkage and expansions of the wood, which neither cracks nor peels.
- Accentuates the natural beauty of the wood.
- Uniform and exceptional final result.
- Easily worked.
- Excellently spread with high performance.

SUBSTRATE PREPARATION

The surface should necessarily be dry, rigid and free from dust, mould, grease or resin before application. The humidity of the wood should be low.

In new wood, remove any oil or resin with **LS-735 SOLVENT** and then treat the knots. In painted wood, remove the old paints or varnishes with **REMOVER**

corrosive and then clean the surface with **LS-735**. Repair all the defects of the wood with the appropriate stucco. Use the suitable sandpaper to smoothen the surface well in parallel with the texture streaks. Remove dust with a damp, non-fluffy cloth. For effective protection of the wood, first apply 1 layer of **STATUS BASEWOOD** substrate wood preservative.

APPLICATION

Stir well the content of the container before use for full homogenization of the product. Sand very lightly with very thin sandpaper and wipe well before application. Apply 1-2 layers of **STATUS NAUTICAL** with the suitable brush, covering well all difficult points of the surface, such as corners, hollows, etc. Work the brush evenly in all directions avoiding overlapping and

always finish painting in parallel to the streaks of the texture. Let it dry well between applications. Sand lightly between the two applications and alongside the texture with thin sandpaper. For preserving-refreshing already varnished surfaces, smooth lightly and apply a layer of **STATUS NAUTICAL**.

DRYING

Touch dry after 3-4 hours.

RECOATING

Recoat after 24 hours. Drying times refer to normal environmental conditions (25°C, humidity 60%). Any difference in environmental temperature and humidity could affect the above times.

SHADES

Available in gloss-transparent.

APPLICATION RATE

12-14 m²/lt on properly prepared surfaces.

APPLICATION TOOLS

Brush or roller.

CLEANING OF TOOLS

Immediately after use clean the brush or the roller with WHITE SPIRIT and then with hot water and detergent. Do not pour the washing liquids on the ground.

PACKAGING

Available in metal containers of 750ml, 2.5lt.

STORAGE

In the original sealed container, in dry places and at temperatures between +5°C and +35°C for 2-3 years after production date.

VOLATILE ORGANIC COMPOUNDS (VOC)

Maximum permissible VOC content (Directive 2004/42/EC) for Interior/exterior trim varnishes and woodstains, including opaque woodstains A/e (SB): 400 gr/lt.

- Maximum VOC content in product ready for use: 395 gr/lt.
- Maximum dilution: 3%.

APPLICATION TEMPERATURE

Avoid painting at temperatures lower than 5°C or before rain. During application the surface should not be directly exposed to sunlight.

Adverse conditions during or shortly after application could affect the final properties of the product.

The technical information and guidelines in this brochure related to the application and end-use of THRAKON products are based on the Company's current expertise and experience on the products and are given in good faith provided they are properly stored, used and applied in accordance with the guidelines given by THRAKON. Given that we are unable to directly inspect the conditions that prevail at the worksite as well as the application of the product, the Company shall not provide any guarantee regarding the suitability of its products for any particular purpose and disclaims any legal responsibility that is based on written information in this brochure or on written or oral or otherwise provided recommendations and guidelines. By applying the product on a small surface, the users are advised to test the product's suitability for the intended application and purpose. THRAKON reserves the right to amend the properties of its products without prior notice. All orders are accepted only after acceptance of the above and under the Company's respective Trade Policy terms. This version of the technical data sheet automatically cancels any previous version.

STATUS NAUTICAL YACHT VARNISH



PRECAUTIONS

For information about safe use, storage and disposal of the product read the information on the label and in the most recent MSDS of the product, which is available upon request to the professionals.

The remains of the paints should not be disposed of together with domestic waste. Ask for advice from the local government with regard to the disposal and removal of waste.

Poisoning Centre Tel. No.: 210 77.93.777

| TECHNICAL CHARACTERISTICS | UNITS | STANDARD | VALUE |
|---|---------------|-------------------|-------------|
| Density (20°C) | (g/ml) | EN ISO 2811.01-02 | 0.90 ± 0.05 |
| Viscosity | (sec) | Flow Cup N°4 | 150 ± 30 |
| Dilution with white spirit or oil of turpentine | (% by volume) | | Up to 3% |

Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative Humidity 50 % and without ventilation. They may vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation and absorbability of the substrate.