

STATUS ONE COVER LIGHT ACRYLIC PUTTY READY FOR USE



DESCRIPTION

The **STATUS RUSTBLOCK GLOSS** is an anticorrosive solvent-based enamel, specially designed to be applied to rusted surfaces without prior use of red lead or other anticorrosive substrate. The advanced formulation ensures strong protection against

rust in any new or old metal surface. Exhibits high adhesion and very good leveling and offers excellent resistance to ultraviolet radiation and adverse weather conditions. The result is a glossy, highly durable surface, with nuances intact for a long time.

APPLICATION

Suitable for paint and rust protection of all kinds of new and old metal

surface such as doors, railings, metal trellises, elevators, agricultural machinery, etc.

ADVANTAGES - FEATURES

Excellent corrosion protection.
There is no need for minium or other anti-rust primer.
• Creates surfaces with gloss, hardness and resistance to extreme weather and mechanical stresses.
Strong adhesion.

- Excellent leveling and workup.
- UV resistance.
- Excellent coverage.
- Keeps the nuances of color invariant over time.
- High performance.

SUBSTRATE PREPARATION

The surface must necessarily be sound, dry and free from dust, grease, or rust, to ensure good adhesion. Remove all loose or peeling old paint. Previously painted surfaces should be rubbed with sandpaper and dusted well. In non-ferrous metal surface (galvanized, aluminum, chromium,

bronze or copper), **WASH PRIMER** is applied first and then **OPTIMUM METAL PRIMER**. In addition, to ensure maximum corrosion protection especially in aggressive environments such as coastal and industrial areas or northern sides, first paint with anticorrosive primer **STATUS** or **STATUS MINIO**.

APPLICATION

Stir well before use, dilute and apply the appropriate **STATUS RUSTBLOCK POLISHED**, 2 hands in thick layers with particular attention to the full coverage of difficult points, such as corners, recesses, etc., to avoid possible ingress of moisture causes oxidation. To

ensure maximum protection from rust should the film thickness is at least 100-120mm. After the application close well the container to maintain in good condition for future use. Can be stored in a tightly closed container, without any problem for a long time.

DRYING

Dries out after 1.5 -2 hours, so as not to leave stains on touch

RECOATABILITY

The repainting should be done within three hours. Otherwise, recoating can be done after a minimum of seven days. The drying times refer to normal ambient conditions (25 ° C, 60% humidity). Any differences in temperature and humidity of the environment can alter the above times.

COLOURS

Available in white, black and in 8 shades swatches.

CONSUMPTION

6-8 m² / lt, depending on the texture and porosity of the surface.

TOOLS APPLICATION

Brush, roller, or airless spray gun.

CLEANING TOOL

Immediately after use, clean the brush, or roll with **WHITE SPIRIT** and then with hot water and detergent. Clean the gun with acetone, or **NITRO SOLVENT UNIVERSAL LS-735**. Do not empty washings into the groundwater.

PACKAGING

Available in metal containers of 750ml and 2,5lt.

STORAGE

In the original sealed packaging in dry environment at temperatures between +5 ° C and +35 ° C for a long time.

VOLATILE ORGANIC COMPOUNDS (VOC)

- Maximum allowable VOC content (Directive 2004/42/EC) for the product category A / c 'Coatings & exterior walls of mineral substrate, type Y, PHASE II: 500 gr / lt
- Maximum VOC content of the product ready for use: 490 gr / lt.
Maximum 5% dilution.

APPLICATION TEMPERATURE

Do not paint in temperatures below 5 ° C or before rain. During application surface should not come in direct exposure to solar radiation. Adverse conditions during

or immediately after application may affect the final properties of the product..

The technical information and instructions in this brochure relating to the application and end-use of products based on Thrakon up this expertise and experience of the products and are given in good faith when properly stored, handled and applied in accordance with the instructions of Thrakon. Due to the inability to directly inspect the conditions at the construction site and the implementation process of the product, the Company makes no guarantee regarding the suitability of its products for any particular purpose and disclaims any legal responsibility which is based on quoted information in this booklet, written or oral or otherwise provided recommendations and instructions. Users are advised to perform a little test on the product's suitability for the intended application and purpose. Thrakon reserves the right to change the properties of its products without prior notice. All orders are accepted only after the acceptance of the above and under the current terms of trade policy of the Company. The edition of this technical datasheet automatically cancels any previous one.

STATUS RUSTBLOCK GLOSS SPECIAL ANTIRUST ENAMEL



PRECAUTIONS

For information on the safe use, storage and disposal of the product read the information on the label and in the most recent MSDS. MSDS is available upon request to the professionals. The paint leftovers should not be disposed

with household waste. You should seek advice from local authorities on the disposal and collection of waste.
Poisons Information Centre Tel. 210 77.93.777

TECHNICAL CHARACTERISTICS		UNITS	STANDARD	PRICE
Basis				Modified Alkyd Resins
Density (20°C)		(g/ml)	EN ISO 2811.01-02	1,15 ± 0,15
Viscosity		(sec)	Flow Cup N°4	180 ± 30
Gloss (60°)			EN ISO 2813-99	≥ 85
Hardness (König) after 7 days		(sec)	ISO 1522-00	70±15
Adhesion (cross cut)	on metal surface		EN ISO 2409-95	1-2
	on rusty surface			2-3
Αραιώση με	white spirit for application by brush or roller ή with solvent LS-703 for spray application	(% etc.)		5

Note: Measurements are done in laboratory environment at temperature +23° C, RH 50%, and without ventilation. It is possible to vary depending on the conditions at the site such as temperature, humidity, ventilation and absorbency of the substrate